

Technical Information Sealing Lacquer



DUPLI-COLOR Sealer is quick-drying, extremely low-wear, friction-free and non-yellowing. The sealer is excellently suitable for wood and wood-similar objects like parquet floor, timber stairs, tables, chairs etc.

Quality and properties

- For interior and exterior
- Quick-drying
- Impact and shock-resistant
- Extremely low-wear
- Friction-free
- Non-yellowing

Physical and chemical data

- **Basis of the binder:** Alkyd resin
- **Colour:** transparent
- **Smell:** solvent
- **Degree of gloss** (at measurement angle 60° acc. to DIN 67530):
satin gloss or matt
- **Efficiency:**
per 250 ml can: 3 m²
per 750 ml can: 9 m²
- **Drying time (at 20°C, 65% relative air humidity):**
Coatable: after 12 hours
Walk-on-able: after 24 hours
The drying time depends on surrounding temperature, air humidity and absorptivity of the wooden ground.
- **Best working temperature and object temperature:**
10 - 25°C
- **Cleaning of tools:** immediately after use with a synthetic thinner
- **Storage stability:**
5 years if appropriate storage provided (=10°-25°C, relative air humidity of max. 60%) in the unopened original container.
Do not store below 5°C
- **Size:** metal tins 250 ml and 750 ml

Environment and labelling

Environmentally compatible: MOTIP DUPLI is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal: Please mind the residue inside the containers. Completely emptied containers can be used for recycling. If cans are not emptied, they should be disposed off as "special refuse".

Labelling: All products of MOTIP DUPLI comply with the current status of their labelling regulations. Classification and distinction takes place by the presently legal form of the **Globally Harmonized System of Classification and Labelling of Chemicals** (GHS) or rather by CLP 1272/2008/EG regulations. Our safety data sheets comply with the current form of REACH 1907/2006/EG, article 31 und appendix II,

Using instructions

Before use, carefully read and observe the warning texts on the label!

Preparation of the ground:

- The surface has to be bearing, dry, clean and free from fat and rust.

Painting:

- 2 paint coats in 4 hours intervals.
- Between the coats we recommend to sand with a fine grain.
- Can be diluted with max. 5 % synthetic thinner.

Disclaimer of liability

This application-technological information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively in the responsibility of the user. MOTIP DUPLI is let off the liability, unless the liability-based incident is caused by a fault incurred to MOTIP DUPLI.

For any further technical questions call our hotline +49 (0) 62 66 75-266 from Monday to Thursday from 9 h a.m. to 3 h p.m. or on Friday until 12 h p.m.

As of February 19, 2018
This release replaces all eventually earlier issued versions.

DUPLI-COLOR 2018

Print date: 25.01.2021

MOTIP DUPLI GmbH | Kurt-Vogelsang-Straße 6 | 74855 Haßmersheim | info@de.motipdupli.com