

Technical Information Glass Fibre Material



presto glass fibre materials are available as web, fleece or mat in different sizes.

Web: Ideal for modeling and repairs of shaped, large components, as flexible and highly scalable.

Fleece: Ideal for small repairs (small rust damage, cracks and holes) as well as for surface coatings. Due to the finely textured surface ideal for exterior body sides.

Mat: Ideal for large-scale works and as well as vibration-stressed components. Stable and dense fiberglass material.

All products for laminating with [presto polyester resin](#).

Quality and properties

Glass-fibre web:

- Especially flexible
- Ideal for model making and mold construction
- Very stable
- Optimal adhesion properties
- For all shaping works on vehicle bodies, motorcycle fairings, caravans, boats, and much more
- Thickness: 0,28 mm +/-5% according to EN DIN ISO 5084
- Weight: 330 g/qm +/-5%

Glass-fibre fleece:

- Finely structured surface
- Optimal adhesion properties
- For all surface works on vehicle bodies, motorcycle fairings, caravans, boats, and much more
- Thickness: 0,30 mm according to EN DIN ISO 5084
- Weight: 30 g/qm

Glass-fibre mat:

- Extremely stable and dense
- Ideal for large-scale works and vibration-stressed parts
- Optimal adhesion properties
- For all shaping works on vehicle bodies, motorcycle fairings, caravans, boats, and much more
- Thickness: 3 mm +/-5% according to EN DIN ISO 5084
- Weight: 225 g/qm +/-5%

Environment and labelling

Environmentally compatible: MOTIP DUPLI is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal: Please mind the residue inside the containers. Completely emptied containers can be used for recycling. If cans are not emptied, they should be disposed off as "special refuse".

Labelling: All products of MOTIP DUPLI comply with the current status of their labelling regulations. Classification and distinction takes place by the presently legal form of the **Globally Harmonized System of Classification and Labelling of Chemicals** (GHS) or rather by CLP 1272/2008/EG regulations. Our safety data sheets comply with the current form of REACH 1907/2006/EG, article 31 und appendix II,

Application

- The object you wish to repair should be de-rusted, clean, dry, fat-free and sanded.
- Lightly sand the surface.
- Cut the glassfibre material depending on size of damaged area, calculate a sufficient overlapping.
- Mix the Polyester resin with hardener(according to information on the label).
- Apply fiberglass material and coat evenly and without bubbles with a brush the mixed polyester resin.
- If you wish to lacquer the surface, we recommend to go on (after drying approx. 20-30 minutes) with [presto plastic Body Filler](#) oder presto flex Fine Filler.

Tips for spray painting

Protect the object and the surrounding area from spray mist. When painting small areas it is recommended that a piece of card is used as a mask, with a hole cut in it slightly larger than the area to be sprayed. The mask should be held 1 to 2 cm from the surface. With this method, the mainly part of the spray mist is brought under control. It recommends to mask parts not to be lacquered, to protect the surrounding against the spray mist.

The aerosol can should have room temperature.

Temperature should range between +10°C and +25°C, max. air humidity 60 %.

Store in a dry place. Protect from direct sunlight and other sources of heat. Use only during dry weather, in places protected from the wind, and in well-ventilated rooms. Follow the warning texts on the labels!

Disclaimer of liability

This application-technological information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively in the responsibility of the user. MOTIP DUPLI is let off the liability, unless the liability-based incident is caused by a fault incurred to MOTIP DUPLI.

For any further technical questions call our hotline +49 (0) 62 66 75-266 from Monday to Thursday from 9 h a.m. to 3 h p.m. or on Friday until 12 h p.m.

As of March 2, 2018

This release replaces all eventually earlier issued versions.

Print date: 21.07.2019

MOTIP DUPLI GmbH | Kurt-Vogelsang-Straße 6 | 74855 Haßmersheim | info@de.motipdupli.com